

## Technische Daten / technical data

Contact  
 phone + 49 521 543-0  
 fax + 49 521 543-148  
 e-mail Sales@delcotex.de

**Artikel-Nummer / article-no.:** **63250-080/720 Delinova N-TPU 160**  
**Material Kette / material warp:** dtex 78 Polyamid 6.6  
**Material Schuss / material weft:** dtex 78 Polyamid 6.6  
**Bindung / weave:** Leinwand / plain L1/1  
**Ausrüstung / finish:** TPU Beschichtung / TPU coating

Prüfmerkmal / parameter	Prüfnorm / test standard	Einheit / unit	Sollwert / nominal value
<b>Fadeneinstellung / thread count</b>			
Kette / warp	DIN EN 1049-2	Fäden/cm / threads/cm	46,50 ± 2,00
Schuss / weft	DIN EN 1049-2	Fäden/cm / threads/cm	33,00 ± 2,00
<b>Flächengewicht / weight</b>	DIN EN 12127	g/m <sup>2</sup>	168,00 ± 15,00
<b>Gewebedicke/thickness</b>	DIN EN ISO 5084	mm	ca. 0,17
<b>Gewebebreite Nutz / usable width</b>	DIN EN 1773	cm	≥ 147,00
<b>Höchstzugkraft / breaking force</b>			
Kette / warp	DIN EN ISO 13934-1	N/5cm	≥ 650,00
Schuss / weft	DIN EN ISO 13934-1	N/5cm	≥ 400,00
<b>Dehnung / elongation at break</b>			
Kette / warp	DIN EN ISO 13934-1	%	≥ 30,00
Schuss / weft	DIN EN ISO 13934-1	%	≥ 30,00
<b>Weiterreißkraft Schenkel/ tearforce ( trouser shaped test)</b>			
Kette / warp	DIN EN ISO 13937-2	N	≥ 6
Schuss / weft	DIN EN ISO 13937-2	N	≥ 8
<b>Lichtechtheit/fastness to artificial light</b>	DIN EN ISO 105-B02	Note/grade	≥ 4
<b>Wassersäule / water column</b>	DIN EN ISO 811	mbar	≥ 2000,00

Die vorstehenden Angaben sind allesamt Durchschnittswerte, die lediglich die technischen Eigenschaften und die chemischen Zusammensetzungen der gelieferten Ware beschreiben. Sie sind keine zugesicherten Eigenschaften im Sinne des BGB. Die Prüfergebnisse beziehen sich ausschließlich auf die Prüfgegenstände. Ohne schriftliche Genehmigung der DELCOTEX darf der Prüfbericht - auch nicht auszugsweise - vervielfältigt werden. Bei den vorstehenden Spezifikationen/Datenblättern/Prüfzeugnissen handelt es sich um Beschaffungsangaben und nicht um Garantien. Auch Haltbarkeitsgarantien werden von uns nicht übernommen. Im Übrigen gelten unsere Allgemeinen Liefer- und Zahlungsbedingungen (siehe [www.delcotex.de](http://www.delcotex.de)).  
 The results refer solely to the test materials. Without authorisation of DELCOTEX it is not allowed to duplicate this document, not even in extracts. Previously stated specifications/data sheets/certificates are only characters and no warranties. Also no warranty in case of durability will be overtaken. Finally, our general delivery and payment conditions are valid (please see [www.delcotex.de](http://www.delcotex.de)).

PA-NR. Alex/08.10.2022