


Technische Daten / technical data

Contact
 phone + 49 521 543-0
 fax + 49 521 543-148
 e-mail Sales@delcotex.de

Artikel-Nummer / article-no.:	67002/361 Delinova ECO 75
Material Kette / material warp:	dtex 167 Polyester recycled
Material Schuss / material weft:	dtex 167 Polyester recycled
Bindung / weave:	Leinwand L1/1
Ausrüstung/finish:	spinnfärbend, AC-Beschichtung, FC-Imprägnierung / spun-dyed, AC-coating, FC-impregnation

Prüfmerkmal / parameter	Prüfnorm / test standard	Einheit / unit	Ist-Wert / actual value
Fadeneinstellung / thread count			
Kette / warp	DIN EN 1049-2	Fäden/cm / threads/cm	43,9
Schuss / weft	DIN EN 1049-2	Fäden/cm / threads/cm	24,0
Flächengewicht / weight	DIN EN 12127	g/m ²	139,74
Gewebebreite / width	DIN EN 1773	cm	155,10
Höchstzugkraft / breaking force			
Kette / warp	DIN EN ISO 13934-1	N/5cm	1380,18
Schuss / weft	DIN EN ISO 13934-1	N/5cm	688,82
Dehnung / elongation at break			
Kette / warp	DIN EN ISO 13934-1	%	31,51
Schuss / weft	DIN EN ISO 13934-1	%	33,68
Weiterreißkraft / tear propagation force (tear strength)			
Kette / warp	EN ISO 13937-2	N	20,01
Schuss / weft	EN ISO 13937-2	N	28,64
Waschkrumpf 4N/A 40°C / wash shrinkage 4N/A 40°C			
Kette / warp	DIN EN ISO 6330	%	0,23
Schuss/weft	DIN EN ISO 6330	%	0,00
Wassersäule / watercolumn	DIN EN ISO 811	mbar	≥ 60,00
Spray-Test / spray test	DIN EN ISO 4920	Note / grade	4-5
Öltest / Oiltest	DIN EN ISO 14419	Note/grade	4-5
Waschechtheit 40°C / fastness to washing 40°C	DIN EN ISO 105-C06	Note / grade	4-5
Wasserechtheit / fastness to water	DIN EN ISO 105-E01	Note / grade	4-5

Artikel-Nummer / article-no.: **67002/361 Delinova ECO 75**

Meerwasserechtheit / fastness to sea water	DIN EN ISO 105-E02	Note / grade	4-5
Reibechtheit / fastness to rubbing			
Trocken / dry	DIN EN ISO 105-X12	Note / grade	4-5
Nass/wet	DIN EN ISO 105-X12	Note / grade	4-5
Schweißechtheit/ fastness to perpiration			
Sauer/acid	DIN EN ISO 105-E04	Note / grade	4-5
Alkalisch/alkaline	DIN EN ISO 105-E04	Note / grade	4-5
Lösemittelechtheit/fastness to organic solvents			
Benzin/ petrol	DIN EN ISO 105-X05	Note/grade	4-5
Perchlorethylen / perchloroethylene	DIN EN ISO 105-X05	Note/grade	4-5
Lichtechtheit / fastness to light	DIN EN ISO 105-B02	Note / grade	5
Pflegekennzeichnung / care labelling	ISO 3758		

Die vorstehenden Angaben sind allesamt Durchschnittswerte, die lediglich die technischen Eigenschaften und die chemischen Zusammensetzungen der gelieferten Ware beschreiben. Sie sind keine zugesicherten Eigenschaften im Sinne des BGB. Die Prüfergebnisse beziehen sich ausschließlich auf die Prüfgegenstände. Ohne schriftliche Genehmigung der DELCOTEX darf der Prüfbericht - auch nicht auszugsweise - vervielfältigt werden. Bei den vorstehenden Spezifikationen/Datenblättern/Prüfzeugnissen handelt es sich um Beschaffenheitsangaben und nicht um Garantien. Auch Haltbarkeitsgarantien werden von uns nicht übernommen. Im Übrigen gelten unsere Allgemeinen Liefer- und Zahlungsbedingungen (siehe www.delcotex.de).

The results refer solely to the test materials. Without authorisation of DELCOTEX it is not allowed to duplicate this document, not even in extracts. Previously stated specifications/data sheets/certificates are only characters and no warranties. Also no warranty in case of durability will be overtaken. Finally, our general delivery and payment conditions are valid (please see www.delcotex.de).

PA-NR. 79976/Alex/05.07.2023

Seite/page 2/2